

ISONEM[®] BD



Transparent Floor Insulation "Non Film Formation"

This product applies insulation without the formation of the film on the surface applied, with full impregnation on the floors or the walls, ensuring full protection, it breathes, is not affected from the UV lights or the sun rays, and is inflammable. It dries up within one hour after the application. It is easy to use, economic and long lasting. It can be applied on all types of surfaces with finished coating, that are absorbent, and that are exposed to water insulation problems.

USING AREAS:

- On terraces coated with ceramic, marble, granite., travertine, etc.
- On balconies and roofs coated with ceramic, tiles, etc.
- In bathrooms, showers, toilets and kitchens
- In swimming pools and thermal springs
- On mosaic coated floors and walls
- On aluminum, concrete and plaster surfaces
- On outer surfaces coated with marble, btb granite mosaic, ceramic, etc.

APPLICATION:

The barrel of ISONEM BD is shaken thoroughly before usage. Then, the product is poured into a plastic bucket and is thoroughly applied on the surface, with the use of a brush, it is applied very carefully particularly on the walls. The surfaces where the product has been applied, is let to dry for about 1 hour. After waiting for one hour, the remains of the product that have not been absorbed (generally, the product remains unabsorbed on glazed ceramic or marble surfaces) are wiped out with a wet piece of cloth. The cleansing operation must be applied with a wet piece of cloth and the use of materials such detergents must be avoided. The use of wet cloth is recommended to avoid the dry up and formation of stains on glazed surfaces such as ceramics or marble. A second layer is applied after waiting for one hour, through the application of the same process, and again, after the lapse of a period of another hour, the ceramic or marble surfaces are wiped with a piece wet cloth, and the application is finished.

USING:

PREPARATION OF THE SURFACE: Any parts that are swollen or cracked on the surface, must be repaired prior to application. The surface is also washed and cleansed from grease, soil, dust or mud. The coatings that have bulged or displaced are repaired and consolidated, if the mastic and silicon applications are worn out or removed, they must be repaired and recovered, and the surface is reworked to become fully prepared for the application, if the floor has been washed, it must be let to dry thoroughly and application is made after the floor is completely dried.

CONSUMPTION: 200 ml/m²

PACKAGING: 5 lt Plastic Barrel

STORAGE CONDITIONS/SHELF LIFE: 18 months from date of production if stored properly in unopened and undamaged original sealed containers at temperatures between +5°C to +35°C at dry conditions. Protect from excessive temperature and frost.

